

## Introduction

Sun Microsphere hollow ceramic microspheres is made of PFA(pulverized fuel ash) by products engineered to specific customers' demands, which offers important benefits .QK150 has a top size of 150 microns. It is a proper product demanded by sealing compound, adhesives and industrial coatings and ceramics.



## Typical properties

Product	Qk150
true density	0.75 g/cc
density	0.39 g/cc
crush strength	4500 psi
D10	45 microns
D50	76 microns
D90	125 microns
top size	150 microns
floating ratio	95%
thermal conductivity	0.08 W/mK
oil absorption	0.5g/cc
pH Value	6-8
melting point	1600 degree C
color	70 WhH *
Hardness	6 Moh's scale
Looks like	free flowing powder

\* WhH = Hunter Lab index

## Chemical Composition

SiO <sub>2</sub>	54%
Al <sub>2</sub> O <sub>3</sub>	41%
Fe <sub>2</sub> O <sub>3</sub>	1.8%
CaO	1.1%
TiO <sub>2</sub>	0.23%
MgO	0.8%
K <sub>2</sub> O	1.2%
Na <sub>2</sub> O	0.5%
Loss on Ignition	0.5%

## Advantages

- ✍ High filler loading;
- ✍ Excellent water resistance;
- ✍ Improved flowability;
- ✍ Low viscosity;
- ✍ Reduced shrinkage and warpage;
- ✍ Highly adaptable to a wide range of product processes

## Package and Storage

Big bag: polypropylene container bag;  
 Typical package size: 1150 x 1150 x 1050mm (height)  
 Typical net weight: 500kg

Paper Bag: 3ply water soluble kraft paper bag;  
 Typical package size: 750 x 400 x 180mm (height)  
 Typical net weight: 20kg

Both types are palletized and wrapped.

Call now to order at

+86 13903150114

